ENECLAD SPS Self Priming Screed

Prime, seal, & smooth rough concrete surfaces in one simple step.

ENECLAD® SPS is a three-component, 100% solids, concrete primer that is specifically formulated to smooth-out rough concrete surfaces in order to improve the appearance of ENECON® *High Performance Polymer System* top-coats such as ENECLAD® FPS or CHEMCLAD® polymer systems. It is easy to apply using a trowel or squeegee. **ENECLAD®** SPS is virtually odor free.

ENECLAD® SPS exhibits excellent adhesion to any type of concrete substrate.











Toll Free: 888-4-ENECON (888-436-3266) Tel: 516 349 0022 · Fax: 516 349 5522

Iel: 516 349 0022 · Fax: 516 349 5522 info@enecon.com 6 Platinum Court · Medford, NY 11763-2251

- No Odor
- 100% Solids
- Excellent Abrasion & Impact Resistance
- Outstanding Adhesion
- Safe & Simple to Use

Technical Data					
Volume capacity per kg.		33 in ³ / 540 cc			
Mixed density		0.065 lbs per in ³ / 1.80 gm per cc			
Coverage rate per 20 kg.					
@ 30 mils / 750 microns		150 ft ² / 14 m ²			
Shelf life		Indefinite			
Volume solids		100%			
Mixing ratio	Base	Activator			
By volume	2	1			
By weight	2.4	1			

Working Life & Cure Times

	pient erature	Working Life	Light Load	Full Mechanical
41°F	5°C	2 hrs	3 days	7 days
59°F	15°C	40 min	6 hrs	36 hrs
77°F	25°C	20 min	4 hrs	24 hrs
86°F	30°C	15 min	3 hrs	16 hrs
59°F 77°F	15°C 25°C	40 min 20 min	6 hrs 4 hrs	36 hrs 24 hrs

Physical Properties	Typical Values	6	Test Method
Compressive strength	11,000 psi	770 kg/cm ²	ASTM D-695
Flexural strength	4,000 psi	280 kg/cm ²	ASTMD-790
Hardness-Shore D	8	38	ASTM D-2240
Tensile shear adhesion			
Steel	2,000 psi	140 kg/cm ²	ASTM D-1002
Elcometer Adhesion - to properly prepared cementitious surfaces is			

Elcometer Adhesion - to properly prepared cementitious surfaces is greater than the cohesive strength of the substrate.

Chemical Resistance					
Acetic acid (0-5%) G Acetone G Ammonia solution (0-10%) EX Aviation fuel EX Butyl alcohol G Calcium chloride EX Crude oil EX Diesel fuel EX	Methyl alcohol G Methyl ethyl ketone G Nitric acid (0-10%) G Palmitic acid EX Phosphoric acid (0-5%) EX Phosphoric acid (5-10%) G Potassium chloride EX Propyl alcohol G				
Ethyl alcohol G Gasoline	Sodium chloride				
Heptane EX	Sulfuric acid (0-50%) G				
Hydrochloric acid (0-10%) EX Hydrochloric acid (10-20%) G	Tannic acid				
Kerosene	Transformer oil				
EX - Suitable for most applications including immersion. G - Suitable for intermittent contact, splashes, etc.					

Using ENECLAD[®] SPS

Surface Preparation - ENECLAD[®] SPS should only be applied to clean, dry, firm and well roughened surfaces.

1. Remove all loose material and surface contamination.

2. Depending on the surface, solvent clean and / or remove contamination by abrasive blasting, steam cleaning, pressure washing, or other suitable means.

3. After removing all surface and sub-surface contamination, flush the area as necessary and allow to dry completely.

Mixing & Application - For your convenience, the ENECLAD[®] SPS Base, Activator and Aggregate have been supplied in precisely measured quantities to simplify mixing of full units. Should a small amount of material be required, measure out 2 parts Base and 1 part Activator by volume (2:1, v/v) and then add Aggregate to achieve the desired consistency. While hand mixing is possible, the use of a mechanical mixing device such as a paint mixer in an electric drill or other suitable device will accelerate the mixing process. Pour the entire contents of both the Base and Activator cans into the large plastic bucket and mix the liquids together. With the mixing device running, slowly add the Aggregate. Continue mixing until a smooth, uniform mixture is obtained. Apply the mixed ENECLAD[®] SPS to the surface using an appropriate tool. While a trowel may be suitable for relatively small areas, the use of a long handled, floor squeegee has been found most effective on larger areas. In either case, press the material in well to eliminate entrapped air and insure thorough contact with the surface. Note: it may be necessary to mix the material repeatedly during the application process to insure uniform distribution of the Aggregate and prevent settling.

Health & Safety - Every effort is made to insure that ENECON[®] products are as simple and safe to use as possible. Normal industry standards and practices for housekeeping, cleanliness and personal protection should be observed. Please refer to the detailed MATERIAL SAFETY DATA SHEETS (MSDS) supplied with the material (also available on request) for more information.

Cleaning Equipment - Wipe excess material from tools immediately. Use acetone, MEK, isopropyl alcohol or similar solvent as needed.

Technical Support - The ENECON[®] engineering team is always available to provide technical support and assistance. For guidance on difficult application procedures or for answers to simple questions, call your local ENECON[®] Fluid Flow Systems Specialist or the ENECON[®] Engineering Center.





All information contained herein is based on long term testing in our laboratories as well as practical field experience and is believed to be reliable and accurate. No condition or warranty is given covering the results from use of our products in any particular case, whether the purpose is disclosed or not, and we cannot accept liability if the desired results are not obtained.

Copyright © 2014 by ENECON® Corporation. All rights reserved. No part of this work may be reproduced or used in any form or by any means - graphic, electronic or mechanical including photocopying, recording, taping or information storage and retrieval systems without written permission of ENECON® Corporation.